

U-90

ENTRANCE EXAMINATIONS, JUNE 2010 QUESTION PAPER

M.Tech./Ph.D.(Nano Science and Technology)

Marks: 75

Time: 2.00 hrs

Hall Ticket no:

- I. Write your Hall Ticket Number on the OMR Answer Sheet given to you. Also write the Hall Ticket Number in the space provided above.
 - II. Read the following instructions carefully before answering the questions.
 - III. This Question paper has TWO parts: **PART 'A' and PART 'B'**
1. **Part 'A':** It consists of 25 objective type questions of one mark each.
There is a negative marking of 0.33 marks for every wrong answer.
The marks obtained by a candidate in this part will be used for resolving tie cases.
 2. **Part 'B':** It consists of 50 objective questions of one mark each.
There is no negative marking in this part.
 3. **All questions are to be answered.** Answers for these questions are to be entered on the OMR sheet, filling the appropriate circle against each question. For example, if the answer to a question is (d), it should be marked as below:

A B C
 4. Hand over both the question paper booklet and the OMR answer sheet at the end of the examination.
 5. Calculators are permitted. Log tables are not allowed. **Mobile phones are not permitted inside the Examination Hall.**
 6. This book contains 18 pages including this cover sheet.

PART 'A'

1. The integral $\int_0^1 xe^x dx$ is equal to

- A. 0
- B. 0.5
- C. 1
- D. 3.5

2. C₆₀ has

- A. 12 pentagons and 18 hexagons
- B. 12 pentagons and 20 hexagons
- C. 10 pentagons and 20 hexagons
- D. 14 pentagons and 18 hexagons

3. $\int \frac{dx}{a+bx}$ is

- A. $\frac{1}{b} \ln(a+bx) + c$
- B. $\ln(a+bx) + c$
- C. $b \ln(a+bx) + c$
- D. $\frac{1}{a} \ln(a+bx) + c$

4. Energy gap of silicon at room temperature is

- A. 0.7 eV
- B. 1.1 eV
- C. 5.0 eV
- D. 1.5 eV

5. "Meisner effect" is associated with

- A. superplasticity,
- B. superelasticity,
- C. superconductivity
- D. superalloys

6. "Bucky balls" are made of

- A. C_{60} molecules
- B. a metallic glass
- C. a polymeric material
- D. superconductors

7. Skin allergy results from the interaction of sweat and other body fluids with

- A. nickel ions
- B. nitrogen ions
- C. titanium ions
- D. none of these

8. Tetragonal phase ZrO_2 can be stabilized down to room temperature by adding a small amount of

- A. Y_2O_3
- B. Be
- C. La
- D. Sn

9. Polygonization is the phenomenon where

- A. dislocations disappear into grain boundaries,
- B. dislocations are generated by the operation of Frank-Read sources
- C. mobile dislocations present in the material are rearranged in cell walls
- D. dislocations form tangles

10. Directional Solidification can be used to produce

- A. creep-resistant materials required for aerospace applications
- B. shape memory alloys
- C. fuel clad tubes for nuclear reactors
- D. materials for Railway axles

11. The lowest density in a powder metallurgy product is its

- A. green density
- B. theoretical density
- C. sintered density
- D. smear density

12. Grain boundary sliding is promoted by

- A. elevated temperatures and decreasing strain rate
- B. elevated temperatures and increasing strain rate
- C. sub zero temperatures and decreasing strain rate
- D. ambient temperature and increasing strain rate

13. Ultimate tensile strength is given by:

- A. maximum load/original area of cross section
- B. maximum load/instantaneous area of cross section
- C. yield load/original area of cross section
- D. yield load/instantaneous area of cross section

14. Elements A and B will form a solid solution under the following condition (a_A , a_B are lattice parameters of A and B respectively)

- A. $|a_A - a_B| > 15\%$
- B. $|a_A - a_B| < 15\%$
- C. $|a_A + a_B| < 15\%$
- D. $|a_A + a_B| > 15\%$

15. Dislocations in metals are characterized by

- A. etch-pitting
- B. transmission Electron Microscopy
- C. both A and B
- D. none of these

16. Hall-Petch slope "k" in the equation, $\sigma_y = \sigma_i + kd^{-1/2}$ will have the units of

- A. no units because it is a constant
- B. N/m^2
- C. $N/m^{1/2}$
- D. $N/m^{3/2}$

17. The following are equilibrium defects

- A. dislocations
- B. vacancies
- C. stacking faults
- D. cracks

18. Dislocation multiplication in polycrystalline materials occurs by the operation of

- A. Cottrell-Bilby source
- B. Johnston-Gilman source
- C. Frank-Read source
- D. Nabarro-Herring source

19. Eutectoid reaction is given by:

- A. $\text{Liquid}_1 \leftrightarrow \text{Solid} + \text{Liquid}_2$
- B. $\text{Liquid}_1 \leftrightarrow \text{Liquid}_2 + \text{Liquid}_3$
- C. $\text{Liquid}_1 \leftrightarrow \text{Solid}_1 + \text{Solid}_2$
- D. $\text{Solid}_1 \leftrightarrow \text{Solid}_2 + \text{Solid}_3$

20. Ellingham diagram is a representative plot between:

- A. ΔG vs T
- B. ΔG vs P
- C. ΔU vs T
- D. ΔU vs P

21. One of the following is correct at room temperature (D is Diffusion Coefficient):

- A. $D(\text{grain boundaries}) < D(\text{lattice})$
- B. $D(\text{grain boundaries}) > D(\text{lattice})$
- C. $D(\text{grain boundaries}) = D(\text{lattice})$
- D. $D(\text{grain boundaries}) / D(\text{lattice}) = \infty$

22. A thermocouple is used to measure temperature. It works on the principle expounded by

- A. Seebeck
- B. Einstein
- C. Raman
- D. Roentgen

23. The number of free electrons in a completely filled energy band is

- A. zero
- B. one
- C. infinite
- D. equal to the number of valance electrons

24. Fermi level of a metal defines

- A. the highest occupied level of electron energies at absolute zero
- B. the lowest occupied level of electron energies at absolute zero
- C. the highest occupied level of electron energies at room temperature
- D. the band gap in an intrinsic semi-conductor

25. A color center is

- A. an atom in a crystal that emits radiation in the visible region
- B. a lattice vacancy in a crystal
- C. a lattice defect in a crystal that absorbs visible light
- D. a type of Frenkel defect

HowToExam.com

PART 'B'

26. To achieve excellent surface finish one resorts to

- A. sand casting
- B. sand blasting
- C. investment casting
- D. slip casting

27. An intermetallic that is superconducting is

- A. Ni_3Al
- B. Nb_3Sn
- C. Ti_3Al
- D. MoSi_2

28. Fuel cells are based on a principle which is the converse of

- A. oxidation,
- B. electrolysis
- C. photosynthesis
- D. None of these

29. Peak strengthening in age hardening Al-Cu alloys is derived from

- A. local clustering of copper atoms
- B. ordering of copper atoms on {100} planes of matrix
- C. formation of coherent precipitate platelets of CuAl_2
- D. the occurrence of an equilibrium phase CuAl_2

30. Near net-shape components are manufactured by

- A. hot isostatic pressing
- B. hot pressing
- C. activated sintering
- D. hydrostatic extrusion

31. The specific heat capacity (C_V) of an insulator at a constant volume V and temperature T is given as

- A. $C_V = AT^3$
- B. $C_V = AT^2$
- C. $C_V = AT^3 + BT$
- D. $C_V = AT^2 + BT$

32. n -type semi-conductor is obtained by doping Si with

- A. B
- B. Al
- C. Ga
- D. Sb

33. The following alloys are used for soldering

- A. Cu-Al
- B. Al-Si
- C. Cu-Zn
- D. Sn-Ag

34. The following is correct in case of nanocrystalline materials with respect to those of conventional grain size

- A. the density is high
- B. the melting point is high
- C. the weight is more
- D. the grain boundary specific area is more

35. Diffusion flux has the units of

- A. no. of atoms/(area . time)
- B. no. of atoms/(volume . time)
- C. no. of atoms/(length . time)
- D. no. of atoms/(mass . time)

36. The yield point phenomenon observed in annealed plain low carbon steel is due to the presence of

- A. carbon
- B. manganese
- C. silicon
- D. phosphorous

37. Wolframite is an important source of

- A. titanium
- B. tantalum
- C. tungsten
- D. thorium

38. For a closed system of fixed internal energy and volume, at equilibrium

- A. Gibbs free energy is minimum
- B. Helmholtz's free energy is minimum
- C. enthalphy is maximum
- D. entropy is maximum

39. The alloying element that facilitates the formation of passive layer in stainless steels

- A. nickel
- B. carbon
- C. niobium
- D. chromium

40. The deeply seated defects in thick components could be detected by

- A. eddy current inspection
- B. liquid penetrant inspection
- C. magnetic particle inspection
- D. ultrasonic inspection

41. Kroll's process produces

- A. titanium
- B. aluminium
- C. cadmium
- D. plutonium

42. Graphite flakes are important microstructural feature in

- A. nodular cast iron
- B. white cast iron
- C. grey cast iron
- D. hypo-eutectoid steel with 0.7% carbon

43. Major strengthening phase in Ni-base superalloys is

- A. gamma-prime
- B. sigma Phase
- C. chromium carbide
- D. eta-phase

44. The concept of entropy is introduced by:

- A. zeroth law of thermodynamics
- B. first law of thermodynamics
- C. second law of thermodynamics
- D. third law of thermodynamics

45. Diffusion in materials occurs because of:

- A. concentration gradient
- B. potential gradient
- C. both A and B
- D. none of these

46. The following method is not used to estimate grain size in materials

- A. ASTM standard chart comparison method
- B. Newton-Raphson method
- C. Heyn's intercept method
- D. Jeffries planimetric method

47. If the grain size of a material is decreased from 40 μm to 40 nm, its oxidation resistance will

- A. not change
- B. increase
- C. decrease
- D. none of these

48. The limit of the sequence $\sqrt{2}; \sqrt{2\sqrt{2}}; \sqrt{2\sqrt{2\sqrt{2}}}; \sqrt{2\sqrt{2\sqrt{2\sqrt{2}}}} \dots$

- A. 1
- B. 2
- C. $2\sqrt{2}$
- D. ∞

49. In the limit $x \rightarrow \infty$, $y = \sqrt{x}(\sqrt{x+4} - \sqrt{x})$ is

- A. 0
- B. 2
- C. $1/2$
- D. does not exist

50. Radiation pyrometers are used

- A. for measurement of radiation dose
- B. for determining viscosity of the liquids
- C. for temperature measurement
- D. for measuring length of rail track

51. Point defects in crystal cannot be produced by

- A. elastic deformation
- B. plastic deformation
- C. quenching from high temperature
- D. irradiation with neutrons

52. A certain buffer solution contains equal concentrations of A^- and HA. The K_b for A^- is 10^{-10} . The pH of the buffer is

- A. 10
- B. 14
- C. 7
- D. 4

53. Calcium fluoride crystallizes in fluorite structure. The coordination number for the cation and anion is respectively

- A. 6, 4
- B. 4, 6
- C. 8, 4
- D. 6, 6

54. A method of removing excess solute from a colloidal solution is by

- A. recrystallization
- B. gas chromatography
- C. distillation
- D. dialysis

55. Among the following molecules, the shortest bond length is to be found in

- A. C_2
- B. F_2
- C. N_2
- D. O_2

56. The included angle between the opposite faces of diamond pyramid indenter used in the Vicker's hardness test is

- A. 0°
- B. 90°
- C. 136°
- D. 180°

57. Sensitization in stainless steels is associated with

- A. depletion of Chromium to less than 12% at grain boundaries
- B. depletion of Nickel to less than 8% at grain boundaries
- C. depletion of Carbon to less than 0.2% at grain boundaries
- D. depletion of Titanium to less than 0.5% at grain boundaries

U-90

58. Jominy-end quench test is used to measure

- A. hardness
- B. hardenability
- C. toughness
- D. stiffness

59. Top-down approach is generally employed

- A. for reducing the particle size of powders
- B. for increasing the particle size of powders
- C. for not altering the particle size of powders
- D. none of the above

60. Glass ceramics by definition must contain

- A. at least 50% crystalline ceramics by volume
- B. 60% glassy material
- C. a fully glassy structure
- D. a fully ceramic material

61. Materials for orthopedic implants are based on

- A. Pb
- B. Mg
- C. Ti
- D. Be

62. The slope of stress-strain curve in the elastic region gives

- A. yield strength
- B. Youngs' modulus
- C. toughenss
- D. resilience

63. To calculate the residual stresses in a material using X-ray diffraction, the following parameter is used

- A. area under the peak
- B. maximum intensity of the peak
- C. full width at half maximum of the peak
- D. full width at full maximum of the peak

64. The term diamond-like-carbon is most commonly used to refer to

- A. amorphous carbon thin films
- B. graphene layers
- C. crystalline diamond composites
- D. all of the above

65. A powder metallurgy processing route is

- A. mechanical alloying
- B. melt spinning
- C. levitation
- D. short peening

66. Pig iron is produced in

- A. Bessemer converter
- B. open hearth furnace
- C. blast furnace
- D. Cupola

67. Electron back scattered diffraction is a technique based on

- A. optical microscopy
- B. scanning electron microscopy
- C. atomic force microscopy
- D. X-ray diffraction

U-90

68. Magnetic flux density is expressed by

- A. Ampere
- B. Volts
- C. Weber
- D. Weber/m²

69. The Reynolds number is the ratio of

- A. inertial forces/Viscous forces
- B. viscous forces/Inertial forces
- C. viscous forces/gravitational forces
- D. gravitational forces/Viscous forces

70. The two elements responsible for the production of nuclear power by fusion are

- A. deuterium and tritium
- B. uranium and plutonium
- C. thorium and plutonium
- D. tritium and uranium

71. Defects in electronic circuits can be studied by

- A. magnetic particle inspection
- B. thermography
- C. ultrasonic testing
- D. holography

72. Differential Scanning Calorimetry is used for the determination of

- A. surface topography
- B. co-efficient of thermal expansion
- C. phase transformations
- D. grain boundary chemical analysis

15

U-90

73. Bronze is an alloy of copper and

- A. gold
- B. silver
- C. tin
- D. zinc

74. The following has the highest Co-efficient of Thermal Expansion

- A. plastics
- B. ceramics
- C. tin
- D. tungsten

75. The type of corrosion that produces localized attack is

- A. pitting corrosion
- B. uniform corrosion
- C. intergranular corrosion
- D. stress corrosion cracking